



Sunbrella Ink Jet 10 Poly Oxford 8 Poly Light 3

When you need printable woven fabric, Sunbrella® Ink Jet, Poly Oxford 8, and Poly Light 3 offer the depth of color and detail you demand in your choice of heavy, medium, or light weights.

Sunbrella Ink Jet 10

Specifically designed for most solvent-based printers, Sunbrella Ink Jet is highly runoff resistant and holds heavy ink without bleed-through. Its natural woven canvas look is highly wrinkle resistant and excellent for long-term use outdoors. In addition, its ultrasonic slit edges yield straight cuts with no fraying; making Sunbrella Ink Jet extremely easy to cut and sew. When applications call for coordinating fabrics, Sunbrella Ink Jet coordinates with over 50 Sunbrella solids.

Poly Oxford 8

For short-term outdoor use, Poly Oxford 8 offers many of the same features as Sunbrella Ink Jet in a more cost-efficient package. Poly Oxford 8 yields good results with a single pass on some machines, plus excellent strength and dimensional stability.

Poly Light 3

When applications call for a sheer, woven textile look, Poly Light 3 delivers. Its polyester yarn provides excellent strength and stability for its light weight, with a nice drape and more movement in the air. Ultrasonic slit edges yield no-fray straight edges, and it's extremely easy to sew.

The QMLS difference

In today's fast-changing marketplace, we know how important it is to have a reliable source. Not just of products, but of knowledge and information. When you choose QMLS, you get someone who's as committed to the quality of your end product as you are. Someone who knows the options inside and out, and can help you choose the one that's best suited to your needs.

Media	Size	Catalog #
Sunbrella Ink Jet 10	54" x 105'	1354
	60" x 180'	1360
Poly Oxford 8	54" x 150'	2454
	60" x 180'	2460
Poly Light 3	54" x 150'	3654
	60" x 180'	3660

See next page for Specifications.

Ordering

Sunbrella Ink Jet 10, Poly Oxford 8, and Poly Light 3 are stocked in all QMLS distribution centers and available for immediate delivery. [Click here](#) to order online, or call 1-800-552-9427.

Information provided here is based on research and is believed to be reliable as of printing date. This information does not constitute a warranty. All material should be tested by purchaser to determine final suitability. Sunbrella is a registered trademark of Glen Raven, Inc. QMLS will not be held responsible for customers' end-use of product. QMLS is available for directions and advice as to proper use and application of our products.



Quality Media & Laminating Solutions, Inc.
285 State Street, Suite One
North Haven, CT 06473
1-800-552-9427 FAX 203 281-6451
info@qmls.com www.qmls.com

Specifications — Sunbrella Ink Jet 10, Poly Oxford 8, Poly Light 3

Sunbrella Ink Jet 10	
<i>Fabric Weight</i>	10 oz per sq yd
<i>Fiber Content</i>	100% acrylic
<i>Fabric Thickness</i>	0.50 mm
<i>Finished Fabric Width</i>	54 or 60 inches
<i>Fabric Construction: Ends</i>	74 each Test method: ASTM D3775-98
<i>Fabric Construction: Picks</i>	34 each Test method: ASTM D3775-98
<i>Bow/Skew</i>	1 inch
<i>Break Strength</i>	Warp = 230 lbs force Filling = 140 lbs force
<i>Tear Strength</i>	Warp = 10 lbs force Filling = 6 lbs force
<i>Fire Retardant</i>	No

Poly Oxford 8	
<i>Fabric Weight</i>	7.8 oz per sq yd
<i>Fiber Content</i>	100% polyester
<i>Fabric Thickness</i>	0.35 mm
<i>Finished Fabric Width</i>	54 or 60 inches
<i>Fabric Construction: Ends</i>	48 each Test method: ASTM D3775-98
<i>Fabric Construction: Picks</i>	33 each Test method: ASTM D3775-98
<i>Bow/Skew</i>	1 inch
<i>Break Strength</i>	Warp = 350 lbs force Filling = 250 lbs force
<i>Tear Strength</i>	Warp = 30 lbs force Filling = 30 lbs force
<i>Fire Retardant</i>	No

Poly Light 3	
<i>Fabric Weight</i>	3 oz per sq yd
<i>Fiber Content</i>	100% polyester
<i>Fabric Thickness</i>	0.10 mm
<i>Finished Fabric Width</i>	54 or 60 inches
<i>Fabric Construction: Ends</i>	76 each Test method: ASTM D3775-98
<i>Fabric Construction: Picks</i>	56 each Test method: ASTM D3775-98
<i>Bow/Skew</i>	1 inch
<i>Break Strength</i>	Warp = 150 lbs force Filling = 100 lbs force
<i>Tear Strength</i>	Warp = 6 lbs force Filling = 6 lbs force
<i>Fire Retardant</i>	No