



## Hard Guard Lustre

Hard Guard Lustre is low-melt adhesive system with UV inhibitors and a unique hard-coat surface that won't scratch or fingerprint.

### Uses

For tradeshow displays of exceptional finish and incredible durability, Hard Guard Lustre is the answer. It's unique lustre finish provides less reflection than satin and more brilliance than matte — and its adhesive provides an extra-strong bond.

### The QMLS difference

Quality comes first at QMLS. We find the best solutions for your mounting and laminating needs and bring them to you... on time and on budget. So you never have to worry about waste, reprinting, or relaminating.

Size	Catalog #
5 mil	25" x 250' 0770920
	31" x 250' 0770930
	38" x 250' 0770935
	43" x 250' 0770940
	51" x 250' 0770950
10 mil	25" x 250' 0771920
	51" x 250' 0771950

### 5 mil Specifications

Gauge	4.65 mil
Film	2.65 mil polyester
Adhesive	2.00 mil coextrusion
Yield	4,940 in/lb
Gloss	90, Gardner, 60°
PET Side Coefficient of Friction	0.40
Heat Seal Initiation Temp	180°F @ 40psi, 0.5 sec dwell
Useable Temp Range	180° to 245°F
UVA Absorption (315-360 nm)	85% minimum Test method Perkin-Elmer Spectrophotometer
UVB Absorption (260-315 nm)	100% Test method Perkin-Elmer Spectrophotometer

### 10 mil Specifications

Gauge	9.50 mil
Film	6.50 mil polyester
Adhesive	3.00 mil coextrusion
Yield	2,320 in/lb
Gloss	90, Gardner, 60°
PET Side Coefficient of Friction	0.40
Heat Seal Initiation Temp	180°F @ 40psi, 0.5 sec dwell
Useable Temp Range	180° to 245°F
UVA Absorption (315-360 nm)	85% minimum Test method Perkin-Elmer Spectrophotometer
UVB Absorption (260-315 nm)	100% Test method Perkin-Elmer Spectrophotometer

### Ordering

Hard Guard Lustre is a QMLS exclusive. It's stocked in all QMLS distribution centers and available for immediate delivery. [Click here](#) to order online, or call 1-800-552-9427.



Quality Mounting & Laminating Systems, Inc.  
285 State Street, Suite One  
North Haven, CT 06473  
1-800-552-9427 FAX 203 281-6451  
info@qmls.com www.qmls.com

Information provided here is based on research and is believed to be reliable as of printing date. This information does not constitute a warranty. All material should be tested by purchaser to determine final suitability. Quality will not be held responsible for customers end use of product. Quality is available for directions and advice as to proper use and application of products.