



Hard Guard Matte

Hard Guard Matte is a low-glare polyester film with a low-melt adhesive system and UV inhibitors.

Uses

For ink jet, plain paper, and photographic prints, Hard Guard Matte adds rigidity and protection from abrasions, moisture, oils, and dirt. It is suitable for single- or double-sided applications, and its high clarity and matte finish eliminate glare and reflections. When images are ink jet printed, our Quality Satin Paper and Ink Jet Coated Media have been specially designed to work with Hard Guard Matte for superior end results.

The QMLS difference

When you choose QMLS, you get the convenience of three fully-stocked distribution centers in Connecticut, Ohio, and Florida — allowing for same-day shipping and next-day delivery on most orders. Plus a follow-up call for every order, telling you when your products shipped, by what method, and when you can expect delivery. If your products are ever backordered, we give you the option of choosing an alternative at no additional cost to you.

Size	Catalog #
12" x 500'	0880200
25" x 500'	0880220
31" x 500'	0880230
38" x 500'	0880235
43" x 500'	0880240
51" x 500'	0880250
55" x 500'	0880260
62" x 500'	0880280

Specifications	
Gauge	3.00 mil
Film	0.48 mil polyester
Adhesive	2.50 mil coextrusion
Yield	9,090 in/lb
Gloss	40, Gardner, 60°
PET Side Coefficient of Friction	0.40
Heat Seal Initiation Temp	170°F @ 40psi, 0.5 sec dwell
Useable Temp Range	190° to 245°F
UVA Absorption (315-360 nm)	85% minimum Test method Perkin-Elmer Spectrophotometer
UVB Absorption (260-315 nm)	100% Test method Perkin-Elmer Spectrophotometer

Ordering

Hard Guard Matte (except 62" width) is stocked in all QMLS distribution centers and available for immediate delivery. 62" width is a custom order and ships in approximately 5 business days. [Click here](#) to order online, or call 1-800-552-9427.



Quality Mounting & Laminating Systems, Inc.
285 State Street, Suite One
North Haven, CT 06473
1-800-552-9427 FAX 203 281-6451
info@qmls.com www.qmls.com

Information provided here is based on research and is believed to be reliable as of printing date. This information does not constitute a warranty. All material should be tested by purchaser to determine final suitability.